



Knight Corporation Technical Information

MAXIMUM RECOMMENDED OPERATING TEMPERATURES (°F)

*Please note that different chemicals and other factors
may affect the temperature ratings below*

GASKET MATERIALS	BUNA N	250°F
	ETHYLENE PROPYLENE	350°F
	VITON	450°F
	TEFLON	500°F
FILTER MEDIA	POLYESTER	300°F
	POLYPROPYLENE	225°F
	NOMEX	400°F
	NYLON	325°F
HOUSING MATERIALS	CARBON STEEL	400°F
	304 STAINLESS STEEL	400°F
	316 STAINLESS STEEL	400°F
	PVC	150°F
	POLYPROPYLENE	150°F

MAXIMUM TEMPERATURE AT STANDARD VESSEL DESIGN PRESSURE.

FOR MORE INFORMATION, CONTACT YOUR REPRESENTATIVE AT KNIGHT CORPORATION.

Although the information contained in this bulletin is accurate to the best of our knowledge, the Knight Corporation makes no guarantee as to the results that may be obtained and assumes no obligation or responsibility because of this information.

